

XP-002389200

Best Available Copy

Best Available Copy

1/1 - (C) EPODOC / EPO
AN - CN-97101189-A
AP - CN19970101189 19970318
DT - I
EC - C04B40/00D4
SCI - C04B40/00D4
FAMN- 5165568
IC - (A)
C04B22/00
(C)
C04B22/00; C04B18/08; C04B24/00
IN - (A C)
TANG MING [CN]; LI ZHIJIAN [CN]
PA - (A)
SHENYANG CONSTRUCTION ENGINEER [CN]
(C)
SHENYANG BUILDING ENGINEERING [CN]
PN - CN1193616 A 19980923
PR - CN19970101189 19970318
LA - en
UNAP- 97101189
UNIN- MING TANG; ZHIJIAN LI
UNPA- SHENYANG CONSTRUCTION ENGINEERING COLLEGE, SHENYANG BUILDING
ENGINEERING COLLEGE
UNPN- CN 1193616 A
CN 1061328 C
XEC - C04B-040/00D004
XIC - C04B-022/00; C04B-040/00; C04B-018/08; C04B-024/00
AB - (A)
A process for preparing additives of concrete with ultrafine powdered
coal ash includes such steps as grinding powdered coal ash its
specific surface area is not less than 1 sq.m/g and mixing naphthalene
water-reducing agent, wood calcium and ultrafine powdered coal ash in
ratio of 1 : (0.2-0.5) : (8-25) to obtain pumping agent of concrete,
or mixing naphthalene water-reducing agent with the powdered coal ash
in ratio of 1 : (8-25) to obtain additive of high-strength concrete,
or mixing alumina, MC, water-reducing agent and ultrafine powdered
coal ash in ratio of 1 : (3-5) : (3-5) : (20-50) to obtain
water-proofing agent.
ICAI- (A C)
C04B40/00
ICCI- (A C)
C04B40/00
INW - (A C)
TANG MING [CN]; LI ZHIJIAN [CN]
NPR - 1
OPD - 1997-03-18
PAW - (A)
SHENYANG CONSTRUCTION ENGINEER [CN]
(C)
SHENYANG BUILDING ENGINEERING [CN]
PD - 1998-09-23